

City of Mt. Pleasant  
SPECIAL PROVISION  
FOR  
**HMA APPLICATION ESTIMATE - LOCAL STREET**

City of MtPleasant

1 of 1

April 12

**A) Description**

This work shall be done in accordance with the requirements of section 501 of the 2012 Standard Specifications for Construction and applicable supplemental specifications and special provisions, and as specified herein. The HMA Approach bid item shall include paving of HMA Driveways and cross streets. Cross streets shall be constructed in two passes at the same cross-section as the mainline pavement, follow the procedures outlined in MDOT 501.03F4

**B) Materials**

The HMA leveling course and HMA Approach shall be HMA, 13A. The HMA top course shall be HMA, 36A.

The leveling course shall have a yield of 175 pounds per square yard and the binder shall be PG 56-28

The top course shall have a yield of 125 pounds per square yard, an AWI of 260, minimum, and the binder shall be PG 58-28.

HMA Approach shall be 13A. Cross streets shall be constructed in two passes, have a yield of 300 pounds per square yard, and the binder shall be PG 58-28. Driveways shall be constructed in one pass, have a yield of 220 pounds per square yard, and the binder shall be PG 58-28.

The HMA Bond Coat material shall be per Section 501.03. The uniform rate of application shall be 0.05 - 0.15 gallons per square yard.